

Chemical Resistant

XPOSURE GUARD™ C1 Protective Outer Wear

We've got you covered. To learn more, give us a call:

334-899-4351

Chemical Challenge	CAS#	Test Method	Xposure Guard C1- Barreir Film Laminate
Acetone	67-64-1	ASTM F739	imm.
Acetonitrile	75-05-8	ASTM F739	imm.
Ammonia Gas	7664-41-7	ASTM F739	imm.
Black Liquor	66071-92-9	ASTM F739	>480 minutes
1,3-Butadiene Gas	106-99-0	ASTM F739	imm.
Carbon Disulfide	75-15-0	ASTM F739	imm.
Chlorine Gas	7782-50-5	ASTM F739	imm.
Dichloromethane	75-09-2	ASTM F739	imm.
Diethylamine	109-89-7	ASTM F739	imm.
Dimethyl Formamide	68-12-2	ASTM F739	NT
Ethyl Acetate	141-78-6	ASTM F739	imm.
Ethylene Oxide Gas	75-21-8	ASTM F739	imm.
Green Liquor	68131-30-6	ASTM F739	>480 minutes
n-Hexane	110-54-3	ASTM F739	imm.
Hydrogen Chloride Gas	7647-01-0	ASTM F739	imm.
Methanol	67-56-1	ASTM F739	imm.
Methyl Chloride Gas	74-87-3	ASTM F739	imm.
Nitrobenzene	98-95-3	ASTM F739	NT
Phosphoric Acid	7664-38-2	ASTM F739	>480 minutes
Sodium Hydroxide 50%	1310-73-2	ASTM F739	>480 minutes
Sulfuric Acid 98%	7664-93-9	ASTM F739	>480 minutes
Tetrachloroethylene	127-18-4	ASTM F739	imm.
Tetrahydrofuran	109-99-9	ASTM F739	imm.
Toluene	108-88-3	ASTM F739	imm.
White Liquor	68131-33-9	ASTM F739	>480 minutes

Chemical Challenge	CAS#	Test Method	Xposure Guard C1- Barreir Film Laminate
Off Road Diesel	68476-34-6	ASTM F903	Pass, >60 minutes
Formaldehyde	50-00-0	ASTM F903	Pass, >60 minutes
Nitric Acid 70%	7697-37-2	ASTM F903	56 minutes

^{*}imm-immediate breakthrough, NT-Not Tested.